



NEGRO MARQUINA / *BLACK MARQUINA*

## CARACTERISTICAS FISICO-MECANICAS

### *PHYSICO-MECHANICAL PROPERTIES*

<b>PESO ESPECIFICO APARENTE</b>	2,69 G/CM3
BULK SPECIFIC GRAVITY	
<b>POROSIDAD APARENTE</b>	0,47%
APPARENT POROSITY	
<b>COEFICIENTE DE ABSORCION</b>	0,17 %
ABSORPTION COEFFICIENT	
<b>RESISTENCIA MECANICA A LA COMPRESION</b>	629 KG/CM2
COMPRESSION STRENGTH	
<b>RESISTENCIA MECANICA A LA FLEXION</b>	136 KG/CM2
BENDING STRENGTH	
<b>RES.COMP.DESPUES DE LA HELADICIDAD</b>	595 KG/CM2
C.STRENGTH AFTER FREEZING TEST	
<b>RESISTENCIA AL DESGASTE</b>	2,90 MM
FRICIONAL WEAR TEST	
<b>RESISTENCIA AL IMPACTO</b>	30 CM
IMPACT TEST	