



CARACTERISTICAS FISICO-MECANICAS

PHYSICO-MECHANICAL PROPERTIES

PESO ESPECIFICO APARENTE	2,77 G/CM3
BULK SPECIFIC GRAVITY	
POROSIDAD APARENTE	0,6%
APPARENT POROSITY	
COEFICIENTE DE ABSORCION	0,28 %
ABSORPTION COEFFICIENT	
RESISTENCIA MECANICA A LA COMPRESION	781 KG/CM2
COMPRESSION STRENGTH	
RESISTENCIA MECANICA A LA FLEXION	44 KG/CM2
BENDING STRENGTH	
RES.COMP.DESPUES DE LA HELADICIDAD	683 KG/CM2
C.STRENGTH AFTER FREEZING TEST	
RESISTENCIA AL DESGASTE	4,1 MM
FRICIONAL WEAR TEST	
RESISTENCIA AL IMPACTO	41,25 CM
IMPACT TEST	

DARK EMPERADOR