



ROJO ALICANTE / RED ALICANTE

CARACTERISTICAS FISICO-MECANICAS

PHYSICO-MECHANICAL PROPERTIES

PESO ESPECIFICO APARENTE	2,71 G/CM3
BULK SPECIFIC GRAVITY	
POROSIDAD APARENTE	0,3%
APPARENT POROSITY	
COEFICIENTE DE ABSORCION	0,1 %
ABSORPTION COEFFICIENT	
RESISTENCIA MECANICA A LA COMPRESION	965 KG/CM2
COMPRESSION STRENGTH	
RESISTENCIA MECANICA A LA FLEXION	89 KG/CM2
BENDING STRENGTH	
RES.COMP.DESPUES DE LA HELADICIDAD	856 KG/CM2
C.STRENGTH AFTER FREEZING TEST	
RESISTENCIA AL DESGASTE	2,42 MM
FRICIONAL WEAR TEST	
RESISTENCIA AL IMPACTO	30 CM
IMPACT TEST	