

NEGRO MARQUINA PRIMERA

BLACK MARQUINA FIRST



CARACTERISTICAS FISICO-MECANICAS

PHYSICO-MECHANICAL PROPERTIES

PESO ESPECIFICO APARENTE	2,69 G/CM3
BULK SPECIFIC GRAVITY	
POROSIDAD APARENTE	0,47%
APPARENT POROSITY	
COEFICIENTE DE ABSORCION	0,17 %
ABSORPTION COEFFICIENT	
RESISTENCIA MECANICA A LA COMPRESION	629 KG/CM2
COMPRESSION STRENGTH	
RESISTENCIA MECANICA A LA FLEXION	136 KG/CM2
BENDING STRENGTH	
RES.COMP.DESPUES DE LA HELADICIDAD	595 KG/CM2
C.STRENGTH AFTER FREEZING TEST	
RESISTENCIA AL DESGASTE	2,90 MM
FRICIONAL WEAR TEST	
RESISTENCIA AL IMPACTO	30 CM
IMPACT TEST	



NEGRO MARQUINA COMERCIAL
BLACK MARQUINA COMMERCIAL



CARACTERISTICAS FISICO-MECANICAS
PHYSICO-MECHANICAL PROPERTIES

PESO ESPECIFICO APARENTE BULK SPECIFIC GRAVITY	2,69 G/CM3
POROSIDAD APARENTE APPARENT POROSITY	0,47%
COEFICIENTE DE ABSORCION ABSORPTION COEFFICIENT	0,17 %
RESISTENCIA MECANICA A LA COMPRESION COMPRESSION STRENGHT	629 KG/CM2
RESISTENCIA MECANICA A LA FLEXION BENDING STRENGHT	136 KG/CM2
RES.COMP.DESPUES DE LA HELADICIDAD C.STRENGHT AFTER FREEZING TEST	595 KG/CM2
RESISTENCIA AL DESGASTE FRICTIONAL WEAR TEST	2,90 MM
RESISTENCIA AL IMPACTO IMPACT TEST	30 CM

