

DARK EMPERADOR PRIMERA
DARK EMPERADOR FIRST




CARACTERISTICAS FISICO-MECANICAS
PHYSICO-MECHANICAL PROPERTIES

PESO ESPECIFICO APARENTE BULK SPECIFIC GRAVITY	2,77 G/CM3
POROSIDAD APARENTE APPARENT POROSITY	0,6%
COEFICIENTE DE ABSORCION ABSORPTION COEFFICIENT	0,28 %
RESISTENCIA MECANICA A LA COMPRESION COMPRESSION STRENGHT	781 KG/CM2
RESISTENCIA MECANICA A LA FLEXION BENDING STRENGHT	44 KG/CM2
RES.COMP.DESPUES DE LA HELADICIDAD C.STRENGHT AFTER FREEZING TEST	683 KG/CM2
RESISTENCIA AL DESGASTE FRICTIONAL WEAR TEST	4,1 MM
RESISTENCIA AL IMPACTO IMPACT TEST	41,25 CM



DARK EMPERADOR COMERCIAL
DARK EMPERADOR COMMERCIAL



CARACTERISTICAS FISICO-MECANICAS
PHYSICO-MECHANICAL PROPERTIES

PESO ESPECIFICO APARENTE BULK SPECIFIC GRAVITY	2,77 G/CM3
POROSIDAD APARENTE APPARENT POROSITY	0,6%
COEFICIENTE DE ABSORCION ABSORPTION COEFFICIENT	0,28 %
RESISTENCIA MECANICA A LA COMPRESION COMPRESSION STRENGTH	781 KG/CM2
RESISTENCIA MECANICA A LA FLEXION BENDING STRENGTH	44 KG/CM2
RES.COMPR.DESPUES DE LA HELADICIDAD C.STRENGTH AFTER FREEZING TEST	683 KG/CM2
RESISTENCIA AL DESGASTE FRICTIONAL WEAR TEST	4,1 MM
RESISTENCIA AL IMPACTO IMPACT TEST	41,25 CM

